

CC road® 34%

Calcium chloride road grade liquid



TETRA Chemicals Europe

Box 901, SE-251 09
Helsingborg, SWEDEN
Phone: +46 42 453 27 00
Fax: +46 42 453 27 80
info@tetrachemicals.com

Box 551, FI-67701
Kokkola, FINLAND
Phone: +358 6 8282 111
Fax: +358 6 8282 575

General Description

TETRA Chemicals Europe use selected raw materials in a dedicated production process. CC road® is produced to suit the specific needs of our road maintenance and de-icing customers. Our ISO system ensures that our high standards of production are maintained and improved.

Applications

CC road® is used in various applications within road maintenance. Some examples of common applications are:

- Dust-binding of gravel roads
- Dust-binding of fine particles (PM10) in cities to improve air quality.
- Treatment of gravel roads, tennis courts and hippodromes to suppress dust.
- As an efficient de-icing agent to melt snow and ice on paved and unpaved surfaces.
- Maintenance of gravel roads to stabilize the road surface.

For more information on applications, please visit:
www.tetrachemicals.com

Availability

CC road® 34% is produced in Belgium. It is available as a bulk liquid in tank trucks.

Safety and Handling

Before using this product, refer to the MSDS available on our website for complete safety and handling guidelines.

Physical Properties

Appearance	Clear to slightly yellow
Odor	None
Typical crystallization temperature	-20°C
Typical density at 20°C	1.33 kg/L

Chemical Properties

Parameter	Unit	Specification	Typical value
CaCl ₂ concentration	%	> 34	34.5
pH (in 10% CaCl ₂ solution @ 20°C)	-	9-11	10

www.tetrachemicals.com

Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. Further, nothing contained herein shall be taken as a recommendation to manufacture or use any of the herein described materials or processes in violation of existing or future patents. Copyright © 2010 TETRA Technologies, Inc. All rights reserved. TETRA and the TETRA logo are registered trademarks of TETRA Technologies, Inc. This data sheet replaces all other versions.

